

WELDOX® 1030

Special data sheet

HIGH STRENGTH STRUCTURAL STEEL PLATE

WELDOX 1030 is a general structural steel with a minimum yield strength of 1030 MPa.

Applications Load carrying structures having very high demands on low weight.

Designation WELDOX 1030E with guaranteed impact toughness at -40°C

Chemical composition

(ladle analysis)

C*	Si*	Mn*	P	S	B*	Nb*	Cr*	V*	Cu	Ti	Al* total	Mo*	Ni	N
max %	max %	max %	max %	max %	max %	max %	max %	max %	max %	max %	min %	max %	max %	max %
0,21	0,50	1,60	0,020	0,005	0,005	0,04	0,80	0,08	0,10	0,02	0,020	0,70	2,0	0,010

* Intentional alloying elements. The steel is grain-refined

Plate thickness	CEV	CET	CEV = C + $\frac{Mn}{6} + \frac{Cr+Mo+V}{5} + \frac{Ni+Cu}{15}$
	Typical values	%	
8 mm	0,53	0,34	CET = C + $\frac{Mn+Mo}{10} + \frac{Cr+Cu}{20} + \frac{Ni}{40}$
12 mm	0,59	0,35	

Mechanical properties

Plate thickness mm	Yield strength ¹⁾ R _{p0,2} , min MPa ²⁾	Tensile strength ¹⁾ R _m MPa ²⁾	Elongation ¹⁾ A ₅ min %
4,0 - 4,9	1030	1200 - 1500	8
5,0 - 12,0	1030	1200 - 1500	10

¹⁾ For transverse test pieces

²⁾ 1 MPa = 1 N/mm²

Impact properties

Steel grade and quality	Test temperature °C	Impact energy (J) for test on transverse Charpy V 10 x 10 test specimens ¹⁾ , min.
WELDOX 1030E	-40	27

¹⁾ Average of three tests. Single value min 70% of specified average.

For plate thicknesses less than 12 mm, subsize Charpy V-specimens are used.

The specified minimum value is then proportional to the cross section of the specimen.

Testing

Testing according to EN 10025.

WELDOX 1030

Special data sheet

Delivery condition	Q Quenched or quenched and tempered at our discretion.												
Dimensions	WELDOX 1030 is delivered in plate thicknesses of 4-12mm. More detailed information on dimensions is provided in our brochure 42-General Product Information WELDOX, HARDOX and ARMOX-UK.												
Tolerances	<ul style="list-style-type: none"> - All plates are produced with AccuRollTech™ thickness precision guarantee. <p>AccuRollTech™ meets the requirements of EN 10 029, but offers more narrow tolerances.</p> <ul style="list-style-type: none"> - Tolerances on flatness according to Class N (Normal tolerances). <p>More detailed information is given in our brochure 42-General Product Information WELDOX, HARDOX and ARMOX-UK as well as at www.weldox.com</p>												
surface condition	According to EN 10163-2, Class A, Subclass 1 (repair by welding is allowed).												
General technical delivery requirements	According to our brochure 42-General Product Information WELDOX, HARDOX and ARMOX-UK.												
Heat treatment and fabrication	<p>WELDOX 1030 has obtained its mechanical properties by a quenching process. WELDOX 1030 is not suited for applications requiring hot working at temperatures above 200° C since the material may then lose its guaranteed properties.</p> <p>For information concerning welding and fabrication, see our brochures listed below. You can also visit www.weldox.com or consult our Technical Customer Service.</p> <table border="0"> <tr> <td>Fabrication</td> <td>Brochure No</td> <td>As for steel grade</td> </tr> <tr> <td>Machining</td> <td>E-10</td> <td>WELDOX 1100E</td> </tr> <tr> <td>Welding</td> <td>E-11</td> <td>WELDOX 960E</td> </tr> <tr> <td>Bending, shearing</td> <td>E-12</td> <td>WELDOX 1100E</td> </tr> </table> <p>Appropriate health and safety precautions must be taken when welding, cutting, grinding or otherwise working on the product. Grinding, especially of primer coated plates, may produce dust with high particle concentration.</p>	Fabrication	Brochure No	As for steel grade	Machining	E-10	WELDOX 1100E	Welding	E-11	WELDOX 960E	Bending, shearing	E-12	WELDOX 1100E
Fabrication	Brochure No	As for steel grade											
Machining	E-10	WELDOX 1100E											
Welding	E-11	WELDOX 960E											
Bending, shearing	E-12	WELDOX 1100E											