

Hot rolled Steel Plates, Sheets and Coils

Structural steels

S690 QL

The high-strength S690 QL steel is a quenched and tempered structural grade in compliance with EN 10025-6:2004 and designed to provide good welding and bending properties. The high strength of this steel allows for lighter products and structures.

Applications

- Machine building
- Steel constructions
- Framework structures
- Lifting and mobile equipment
- Vehicles and transport equipment

Ruukki is a metal expert you can rely on all the way, whenever you need metal based materials, components, systems or total solutions. We constantly develop our product range and operating models to match your needs.

The high strength structural steel in the quenched and tempered condition S690 QL is developed to improve the performance, durability and safety of vehicles, lifting equipment and steel structures. Due to the high strength of the steel, structures can be designed lighter, payload increased and energy used more efficiently.

● **Designation**

The letter “S” in the designation S690 QL refers to structural steel. The figure “690” refers to the minimum yield strength in MPa. The letter “Q” refers to quenching and tempering, which is the manufacturing method and delivery condition for this grade. Per definition, the procedure includes quenching and tempering. The letter “L” refers to a low notch toughness testing temperature.

● **Reference standards**

Ruukki’s S690 QL meets the requirements of EN 10025-6:2004 “Hot rolled products of structural steels. Part 6: technical delivery conditions for flat products of high yield strength structural steels in the quenched and tempered condition”. EN 10025-6:2004 supersedes, together with EN 10025-1:2004 (Hot rolled products of structural steels. Part 1: General technical delivery conditions), the preceding standard EN 10137-1:1995 (Plates and wide flats made of high yield strength structural steels in the quenched and tempered or precipitation hardened conditions. Part 1: General delivery conditions) and EN 10137-2:1995 (Plates and wide flats made of high yield strength structural steels in the quenched and tempered or precipitation hardened conditions. Part 2: Delivery conditions for quenched and tempered steels).

● **Delivery condition**

Quenched and tempered.

● **Product shape**

Hot rolled plate.

● **Chemical composition**

Chemical composition is presented in table 1.

● **Carbon equivalent**

Carbon equivalent CEV = 0.65 maximum, in accordance with EN 10025-6.
 $CEV = C + Mn / 6 + (Cr + Mo + V) / 5 + (Ni + Cu) / 15$

● **Mechanical properties**

Mechanical properties are presented in table 2.

● **Plate dimensions**

Thickness 6 – 7.99 mm, width 2000 – 2500 mm.
 Thickness 8 – 20 mm, width 2000 – 3000 mm.
 Length: 2000 – 12000 mm.

● **Tolerances on dimensions and shapes**

Thickness, width and length: EN 10029 Class A.
 Flatness: EN 10029 Class N.

● **Surface quality**

EN10163-2 Class A 3.

● **Inspection documents**

EN 10204:2004 Inspection certificate 3.1.

Flangeability

High-strength quenched and tempered steels have to be handled with special care during workshop processing, such as bending and flanging. The instructions given by the steel supplier and good engineering workshop practice form an essential part of work quality and safety.

Minimum recommended inside bend radii for flanging in room temperature are in accordance with EN 10025-6:

- Axis of bend transverse to the rolling direction: 3 x plate thickness.
- Axis of bend longitudinal to the rolling direction: 4 x plate thickness.

When working S690 QL steel in the engineering workshop, high quality forming technology must be applied. Worn tools, insufficient lubrication, surface defects on plates, and cutting burrs may all reduce the quality. Plates taken from cold storage must be allowed to warm up to room temperature (+20°C) before being bent, as the formability may be considerably reduced at low temperatures.

● **Weldability**

The high strength steel grade S690 QL can be welded using all common manual and automatic welding processes. The weldability is good. Welding is to be carried out in accordance with EN 10025-6:2004 and EN 1011-2 (Welding. Recommendations for welding of metallic materials. Part 2: Arc welding of ferritic steels.) Always make sure that moisture and other sources of hydrogen, such as grease, oil and other impurities, have been removed from the surface of the groove before welding.

● **Preparation of grooves**

The welding grooves can be bevelled either by machining or thermal cutting. Flame, plasma or laser cutting may be used. The geometry of the groove primarily depends on plate thickness and the configuration of the joint.

● **Preheating before welding**

The need for preheating is determined by the general instructions of EN 1011-2. The need for preheating is determined mainly by the chemical composition of the steel and the filler materials, i.e. their hardenability. Additionally, the

combined plate thickness, heat input and hydrogen content of the welding consumables have to be taken into account. In normal engineering workshop conditions, the high strength S690 QL steel may be welded without preheating up to a plate thickness of 10 – 15 mm. According to long welding experience, a slight preheating of ~ +50°C has in many cases proven to be beneficial. Preheating is especially important when welding with low heat input, such as in tack welding or welding of root passes.

- **Welding consumables and avoidance of hydrogen absorption**

Welding consumables should be selected according to the requirements of the application. Joint design, welding position and the requirements of the operating conditions affect the choice. To eliminate the risk of cold cracking, the hydrogen content of the filler metal must be kept as low as possible, which means that only low-hydrogen welding consumables (HD ≤ 5 ml/100 g) can be used. The welding consumables must be protected against moisture during transport, storage and use to avoid hydrogen absorption. If necessary, they must be dried according to the manufacturer's instructions before welding. Examples of recommended consumables are given in Table 3. The consumables in the table are matching, providing choices that lead to the same strength level as in the base material.

Filler metals that are clearly softer than the base material (undermatching) may be used on certain conditions. They are suitable for joints subjected to low loads. The benefit of undermatching welding consumables is that the formability and toughness of the weld metal is better than matching consumables.

- **Heat input**

Welding heat input depends on the strength and toughness requirements of the joint. The thermal cycle of the weld can handily be represented by the cooling time of the joint " $t_{8/5}$ ", which means the cooling time from 800 to 500°C. The recommended $t_{8/5}$ cooling time for steel grade S690 QL is approximately 8 – 20 seconds. This approximately corresponds with arc energies of 1.0 – 1.8 kJ/mm for plate thicknesses of 10 – 15 mm. The ideal heat input range in a given case depends on the plate thickness and the requirements for the joint. The longest permissible $t_{8/5}$ cooling

time (corresponding to maximum permissible heat input) is determined by the impact toughness requirement of the HAZ (Heat Affected Zone) of the joint. Impact toughness is impaired if $t_{8/5}$ and/or heat input exceed their permissible values. The shortest recommended $t_{8/5}$ cooling time (corresponding to minimum permissible heat input) is determined by the susceptibility of the weld metal and the HAZ to cold cracking. If $t_{8/5}$ is too short and/or the heat input too low, the risk of cold cracking increases.

- **Post weld heat treatment (PWHT)**

PWHT is mainly used to reduce the residual stresses after welding and other workshop fabrication. PWHT is not recommended for quenched and tempered high strength steels. The steel grade S690 QL should be post weld heat treated only when this is specified in the design rules of the steel construction.

- **Hot working**

High strength S690 QL steel has obtained its mechanical properties by a quenching and tempering process. S690 QL is not suited for applications requiring hot working at temperatures above 550°C since the material may lose its guaranteed mechanical properties.

- **Flame straightening**

Any flame straightening should be carried out under consideration of the mechanical properties of the steel, which have been achieved by quenching and tempering. In flame straightening, the hot spot temperature must not exceed 550°C, because this could lead to local softening and reduction of strength. Particular care must be exercised if the structure is subject to dynamic loads and thus fatigue damage.

- **Safety instructions**

High strength quenched and tempered steels have to be processed with special care in the engineering workshop. The instructions given by the steel supplier and good engineering workshop practice form an essential part of work quality and safety. Appropriate health and safety precautions must be taken when welding, cutting, grinding or otherwise working high strength S690 QL steel. New employees must receive proper introduction to their duties.

• **Chemical composition**

Table 1

| | Content % (ladle analysis), maximum | | | | | | | | |
|---------|-------------------------------------|------|------|-------|-------|-------|------|------|------|
| | C | Si | Mn | P | S | B | Cr | Cu | Mo |
| S690 QL | 0.20 | 0.80 | 1.70 | 0.020 | 0.010 | 0.005 | 1.50 | 0.50 | 0.70 |

Additionally, niobium (Nb), vanadium (V) or titanium (Ti) may be used as alloying elements either singly or in combination.

• **Mechanical properties**

Table 2

| | Yield strength R _{eH} MPa Minimum | Tensile strength R _m MPa | Elongation % A ₅ Minimum | Impact strength J at -40°C Average minimum |
|---------|--|--|---|--|
| S690 QL | 690 | 770 – 940 | 14 | 30 |

The tensile test is carried out in transversal direction to the rolling direction.

The impact test is carried out in longitudinal direction to the rolling direction.

• **Matching welding consumables**

Table 3

| Welding process | Filler metals ¹⁾ |
|---------------------------------|--|
| Manual metal arc welding (MMAW) | OK 75.75 SH Ni 2 K 90 SH Ni 2 K 100 Fox EV 85 Fox U 100 N |
| Gas metal arc welding (GMAW) | OK Autrod 13.29/M21 ²⁾ Union NiMoCr/M21 ²⁾ Union x85/m21 ²⁾ X70-IG/M21 |
| Submerged arc welding (SAW) | OK Autrod 13.43+OK Flux 10.62 Union S 3 NiMoCr/UV 421 TT Fluxcord 42/OP 121 TT |

¹⁾ Corresponding welding consumables by other manufacturers are also usable.

²⁾ The shielding gas contains approximately 80% argon (Ar) and 20% carbon dioxide (CO₂). Shielding gases with CO₂ content of less than 20% may also be used.

• **Our Customer Service is happy to give you further information**

Sales, technical customer service

info.metals@ruukki.com

Rautaruukki Corporation, P.O. Box 138, FI-00811 Helsinki, Finland.

tel. +358 20 5911

www.ruukki.com

This data sheet is accurate to the best of our knowledge and understanding. Although every effort has been made to ensure accuracy, the company cannot accept responsibility for any loss, damage or other consequence resulting from the use of this publication.

We reserve the right to make changes.

Copyright © 2009 Rautaruukki Corporation. All rights reserved. Ruukki, Rautaruukki, More With Metals and Ruukki's trade names are trademarks or registered trademarks of Rautaruukki Corporation.